



Physical Property	Typical Value	Test Method
Application Temperature (Ambient)	May be applied at low temperature	-
Colour	Black	-
Coverage	2-10 m ² /l (100 to 500 ft ² /gal.) depending on porosity of surface	-
Drying Time	@ 50% R.H. 20 °C Dry Substrate Touch Dry -One hour Firm Dry – 8 to 24 hours	-
Flammability	Wet – Combustible, Dry - Burns	-
Service Temp (coated face)	-30 °C to 85 °C (-22 °F to 185 °F)	-
Solids by Volume	37% (approx.)	-
Solids by Weight	0.87 kg/l (approx.) (8.7 lbs./gal.) [7.2 lbs. /US gal.]	-

Approvals and Certifications

Complies with CGSB 37-GP-9M and ASTM D-41, Type II

Description

910-01 is a quality penetrating primer of thin brush or spray consistency.

Product Size

5 gallon (18.93L) – 39.1 lb

Usage

For priming and sealing dusty, absorbent surfaces to improve bonding of asphalt coatings and finishes. Used for priming thermal insulation, concrete, masonry, gypsum, asbestos, asphalt roofing felts and similar surfaces.

Application

Prep: Surfaces must be dry and free from dust, dirt, grease and other foreign matter.

Apply by brush, roller or spray. Protect new work from open flame or adjacent welding activity. Avoid use where solvent odours may taint food or other susceptible products. Do not apply over coal-tar coatings. Do not apply to wet surfaces.

Clean-up

Use mineral spirits.

Caution

Contains flammable solvents. Take suitable fire precautions. Do not allow smoking or welding in working area. Keep away from heat and open flame. Use in well-ventilated areas. Keep containers covered when not in use. Harmful if swallowed.

For more information, visit www.henry.com or for technical assistance call us at 800-486-1278. For more information on Henry® product warranty and liability disclaimer please visit www.henry.com/warranty. Refer to the Safety Data Sheet prior to using this product. The Safety Data Sheet is available at www.henry.com or by emailing Henry® Product Support at productsupport@henry.com or by calling 800-486-1278.

® Henry is a registered trademark of Henry Company

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry® Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.