



TECHNICAL DATA SHEET
**B.K. Airport & All Season
Asphalt Driveway Sealer 130**

Physical Property	Typical Value	Test Method
Appearance	Black liquid	-
Application Temperature (Ambient)	4 °C (39 °F) and rising	-
Brookfield Viscosity	1600-2000 cPs	-
Drying Time @ 50% R.H. 20 °C (68 °F)	Dry to touch in 1 hour	-
Flash Point	>100 °C (212 °F)	-
Freezability	Do not freeze	-
Solids Content By Weight	58-60%	-
Specific Gravity @ 25 °C (77 °F)	1.09-1.15	-
VOC Content (maximum)	50 g/l	-
Weight Per Gallon	9.1-9.6 lbs	-

Features

- Apply every 5 years
- Easy to apply all seasons from 4 °C (39 °F) to 50 °C (122 °F)
- Fast cure – drive ready and rain safe in 12 hours
- Rubberized for longer life
- Provides a tough, UV-resistant barrier against the elements

Application

Step 1:

Clean: Clean loose debris from pavement with broom and rinse with a garden hose. Remove grease and oil with **Airport Grade™ Multi-Purpose Driveway Cleaner** or detergent. Treat chemical spills with **Airport Grade™ Oil Spot Primer**.

Step 2:

Prep: Repair all cracks and holes and allow to cure thoroughly. For cracks up to 6 mm (1/4"), use **Airport Grade™ Asphalt Driveway Crack Filler** or **Airport Grade™ Depression Filler**. For cracks up to 12 mm (1/2"), use **Airport Grade™ Depression Filler**. Over 12 mm (1/2"), use **Airport Grade™ Pot-Hole Filler**.

Step 3:

Seal: Mix thoroughly using wooden paddle or powered paint mixer. Apply undiluted to a dry and frost-free surface with brush side of a squeegee in 3 to 4 foot sections using a cross pattern to coat evenly. Smooth out ridges and excess sealer. Product cures to a rich black color. This rich, black finish provides a tough, UV-resistant barrier against the elements. Apply in a single, even coat. Multiple coats or applying too thickly will cause slow curing and cracking.

Cure time: Cures to the touch in 1 hour. Light foot traffic in 4 hours. Normally drivable in 12 hours.

NOTE: Do not use on concrete or asphalt less than 6 months old. Do not mix with coal tar pitch or asphalt/solvent based sealer. Do not dilute. Do not apply if rain or temperatures below 4 °C are forecast in less than 12 hours. When transporting, make sure the pail is secured and the lid is tight to prevent spills. Close container after each use.

Coverage

23 to 38 sq. m (250-400 sq. ft.) per 17.0 L pail. Coverage may vary according to surface age, porosity, weather conditions and application method.

Clean-up

Clean uncured sealer with water. For cured sealer, use biodegradable terpene solvent.

B.K. Airport & All Season Asphalt Driveway Sealer

Packaging

18.93 L (5 Gallon)

Colors

Black brown

For more information, visit www.henry.com or for technical assistance call us at 800-486-1278. For more information on Henry's® product warranty and liability disclaimer please visit www.henry.com/warranty. Refer to the Safety Data Sheet prior to using this product. The Safety Data Sheet is available at www.henry.com or by emailing Henry® Product Support at productsupport@henry.com or by calling 800-486-1278.

Henry is a registered trademark of Henry Company.

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry® Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.