

## Blueskin® WP200

### Self-Adhered Waterproofing Membrane

**Physical Properties: Conforms to CCMC 13297-R for use as a waterproofing membrane**

-Colour	Blue	-Flexibility at -25°C (ASTM D1970)	Pass
-Thickness	1.5 mm (60 mils)	-Water Vapour Transmission (ASTM E96)	1.14 ng/Pa.s.m <sup>2</sup> (0.02 perms)
-Application Temp	-10°C and above	-Lap Peel Strength @ 5°C (ASTM D1876)	580 N/m (3.3 lbf/in)
-Elongation (ASTM D412)	300% (To ultimate failure of rubberized asphalt)	-Hydrostatic Head (ASTM D5385)	70 m of water
-Tensile Strength ASTM D412 – modified	2.24 MPa	-Moisture Absorption (ASTM D570-81)	0.1% maximum
-Peel Strength (ASTM D903)	1576 N/m		
-Minimum Puncture Resistance – Membrane (ASTM E154)	222 N/m		

**Packaging**

-Thickness	1.5 mm (60 mils)	-Gross Coverage 914 mm (36")	18.6 m <sup>2</sup> (200 ft <sup>2</sup> )
-Roll Length	20.3 m (66.7 ft.)	-Net Coverage* 914 mm (36")	17.3 m <sup>2</sup> (186 ft <sup>2</sup> )
-Roll Width	914 mm (36")		
-Top Surface	Blue cross-laminated polyethylene (HDPE)		
-Bottom Surface	Siliconized Release Film	*Based on 65 mm laps both sides and end laps.	

**Description**

**Blueskin® WP200** is a self-adhering membrane which consists of an SBS rubberized asphalt compound which is integrally laminated to a blue, high density cross-laminated polyethylene film. **Blueskin® WP200** is specifically designed to be self-adhered to a prepared substrate providing a high-performance waterproofing barrier.

**Features**

- SBS rubberized membrane flexible at low temperatures
- Fully adhered system prevents lateral water movement
- No flame required
- Factory controlled thickness
- Low odour during application

**Uses**

**Blueskin® WP200** is designed for use on concrete foundation walls, plaza decks, tunnels, and parking decks in both vertical and horizontal orientations. **Blueskin® WP200** is an ideal membrane for use in interior applications such as mechanical rooms, laboratories and wet-rooms.

## Blueskin® WP200 Self-Adhesive Waterproofing Membrane

---

### Limitations

---

Non-resistant to oils and solvents. Not designed for use in direct contact with potable water or permanent exposure and must be covered to prevent damage from sunlight. Good practice calls for the membrane to be covered immediately following application. Refer to minimum cure time requirements of sealant and mastics prior to applying polystyrene insulation. Use **HE925 BES Sealant** with polystyrene form foundations. Do not use in contact with flexible PVC/vinyl products. Use only HE925 BES Sealant, Polybitume 570-05 or other Henry approved sealant for terminations and penetrations to ensure sealant compatibility.

### Storage

---

Store **Blueskin® WP200** on original pallets or elevated platform. Protect from weather elements or store in an enclosed area below 40°C and above -10°C. Double stacked pallets are not recommended. If double stacking is necessary, use a plywood sheet to distribute the load.

### Preparation

---

Acceptable substrates are cast-in-place concrete, precast concrete, wood, concrete block, and polystyrene insulation form foundations. Parging of concrete blocks is not required. All surfaces to receive **Blueskin® WP200** must be clean of oil, dust and excess mortar. Concrete surfaces must be smooth and without large voids, spalled areas or sharp protrusions. Concrete must be cured to a minimum of 7 days and must be dry and free from frost before **Blueskin® WP200** is applied. Structural lightweight concrete must be cured 14 days. Where curing compounds are used they must be clear resin based, without oil, wax or pigments.

Prime substrate using **Bakor Aquatac™ Emulsion Primer** applied by spray or roller at a rate of 7 m<sup>2</sup>/litre (300ft<sup>2</sup>/3.78L can) and allow to dry thoroughly before applying **Blueskin® WP200**. In cold weather applications substitute with **Bakor Hi-Tac™ Construction Adhesive and Primer** or **Blueskin® Adhesive** applied at a rate of 80 to 250ft<sup>2</sup> / gal. U.S. Primed surfaces not covered by membrane during the same working day must be reprimed.

### Application

---

**Blueskin® WP200** should be conditioned at room temperature for ease of application.

Refer to **Blueskin® WP200** Guide Specification for detailed application information.

**Where polystyrene foundation forms are used, POLYBITUME® 570-05 Polymer Modified Sealing Compound must be replaced with HE925 BES Sealant.**

**Joint and Crack Treatment:** All cracks in concrete 1.5 mm to 3 mm wide are to be pre-treated with a 1.5 mm (60 mil) coating of **POLYBITUME® 570-05 Sealing Compound** 50 mm wide centered on the crack. Alternately, apply a 150 mm wide strip of **Blueskin® WP200** centered over crack. Provide 75 mm end laps. Horizontal to vertical inside corner transition areas are to be pre-treated with a **POLYBITUME® 570-05 Sealing Compound** fillet extending 19 mm vertically and horizontally from the corner. Apply a minimum 225 mm strip of **Blueskin® WP200** centered at the joint. All outside corners are to be pre-treated with a minimum of 225 mm strip of **Blueskin® WP200** centered at the joint.

**Drains:** At drains, apply **Blueskin® WP200** collar centered on drain and extend 150 mm beyond flange onto deck. Apply field membrane in full width centered over drain. Apply clamping ring in a 1.5 mm (60 mil) bed of **POLYBITUME® 570-05 Sealing Compound**.

**Projections:** Extend **Blueskin® WP200** tight to projection and seal with **POLYBITUME® 570-05 Sealing Compound** extending 50 mm along projection and 50 mm onto **Blueskin® WP200**.

**Vertical Applications:** Apply **Blueskin® WP200** to prepared substrate in lengths of 2400 mm or less. Provide 65 mm laps at both sides and ends. Position for alignment and remove protective film. Press firmly into place. Promptly roll all laps with a counter top roller to effect seal. If more than one length is required on a vertical surface, apply a shingle fashion. Terminate membrane using **POLYBITUME® 570-05 Sealing Compound**, termination bar, reglet or counter flashing as indicated. Refer to manufacturers standard details. All laps within 300 mm of 90° change in plane are to be sealed with **POLYBITUME® 570-05 Sealing Compound**.

**Horizontal Applications:** Apply **Blueskin® WP200** to prepared substrate beginning at the low point of the surface and working to the high point in a shingle fashion. Provide 65 mm side and end laps. Roll membrane immediately over entire surface to effect seal. At all terminations and T-joints, seal laps using **POLYBITUME® 570-05 Sealing Compound**. All laps within 300 mm of a 90° change in plane are to be sealed with **POLYBITUME® 570-05 Sealing Compound**.

For optimal adhesion on applications below 5°C, **Blueskin® WP200** waterproofing membrane should be applied within one hour of the primer application.

### **Protection of Membrane**

---

It is recommended to protect **Blueskin® WP200** in both horizontal and vertical areas. **Bakor 990-31 Protection Board** may be used for most applications. **Henry DB** prefabricated drainage composites or **Asphaltic Protection Board** can also be used for additional protection.

### **Limited Warranty**

---

**LIMITED PRODUCT WARRANTY AND LIABILITY DISCLAIMER:** Many factors affect the results obtained from this product – such as weather, workmanship, equipment utilized, and prior condition of the substrate – and these are all beyond our control. We, the manufacturer, warrant only that we will replace, at no charge, any product proved to have a material defect in original manufacturing within 12 months of purchase, provided the product has been applied in accordance with our written directions for uses we recommend as suitable for this product. Proof of purchase must be provided. **DISCLAIMER OF CONDITIONS/WARRANTIES AND LIMITATION OF LIABILITY:** THIS LIMITED WARRANTY IS IN LIEU OF ANY OTHER CONDITIONS OR WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY IMPLIED CONDITION OR WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. NO ONE, INCLUDING THE MANUFACTURER, SHALL HAVE ANY LIABILITY OF ANY KIND, INCLUDING FOR NEGLIGENCE OR FOR DIRECT, CONSEQUENTIAL, OR INCIDENTAL DAMAGES, RESULTING FROM ANY MISUSE, DEFECTS, ANY DELAYS CAUSED BY REPLACEMENT, OR OTHERWISE BEYOND PRODUCT REPLACEMENT. IF PURCHASER DOES NOT ACCEPT THESE TERMS, PURCHASER MAY RETURN ALL CONTAINERS OR PACKAGES OF PRODUCT PURCHASED FOR A FULL REFUND WITHIN 30-DAYS OF PURCHASE. RETENTION OF PRODUCT BEYOND 30-DAYS, OR USE OF PRODUCT SHALL CONSTITUTE ACCEPTANCE OF THESE TERMS, CONDITIONS, AND DISCLAIMERS. THIS LIMITED WARRANTY AND LIABILITY DISCLAIMER PROVIDES THE PURCHASER'S EXCLUSIVE REMEDY, FROM ANYONE, FOR ANYTHING RELATING TO THE PRODUCT. To the extent that any part of this LIMITED PRODUCT WARRANTY AND LIABILITY DISCLAIMER is determined unenforceable under the law of the place of purchase of the product, that part is severed and the remainder of these terms remain in full force and effect. To the extent permitted by law, the duration of any implied conditions or warranties is limited to the duration of Henry's express warranty.

### **Statement of Responsibility**

The technical and application information herein is based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use. Henry Company data sheets are updated on a regular basis; it is the user's responsibility to obtain and to confirm the most recent version. Information contained in this data sheet may change without notice.